

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08F 4/651, 4/654, 10/00	A1	(11) International Publication Number: WO 99/57160 (43) International Publication Date: 11 November 1999 (11.11.99)
(21) International Application Number: PCT/EP99/02914 (22) International Filing Date: 29 April 1999 (29.04.99) (30) Priority Data: 98201467.2 6 May 1998 (06.05.98) EP (71) Applicant: MONTELL TECHNOLOGY COMPANY B.V. [NL/NL]; Hoeksteen 66, NL-2132 MS Hoofddorp (NL). (72) Inventors: MORINI, Giampiero; Via Giotto, 36, I-35100 Padova (IT). BALBONTIN, Giulio; Via Ugo Bassi, 17/A, I-44100 Ferrara (IT). VITALE, Gianni; Via Fulvio Testi, 22, I-44100 Ferrara (IT). (74) Agents: ZANOLI, Enrico; Montell Italia S.p.A., Via Pergolesi, 25, I-20124 Milano (IT) et al.		(81) Designated States: AU, BG, BR, CA, CN, CZ, HU, ID, IL, IN, JP, KR, MX, NO, PL, RO, RU, SG, SK, TR, UA, VN, ZA, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS (57) Abstract The present invention relates to catalyst components for the polymerization of olefins comprising a titanium compound, having at least a Ti-halogen bond, and at least two electron donor compounds supported on a Mg dihalide, said catalyst component being characterized by the fact that at least one of the electron donor compounds is selected from ethers containing two or more ether groups which are further characterized by the formation of complexes with anhydrous magnesium dichloride in an amount less than 60 mmoles per 100g of MgCl ₂ and by the failure of entering into substitution reactions with TiCl ₄ or by reacting in that way for less than 50 % by moles, and at least another electron donor compound is selected from esters of mono or polycarboxylic acids. Said catalyst components are able to produce propylene polymers which, for high values of xylene insolubility, show a broad range of isotacticity.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

“CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS”

The present invention relates to catalyst components for the polymerization of olefins, in particular propylene, comprising a Mg dihalide based support on which are deposited a Ti compound having at least one Ti-halogen bond and at least two electron donor compounds selected from specific classes. The present invention further relates to the catalysts obtained from said components and to their use in processes for the polymerization of olefins. The catalysts of the present invention are able to give, with high yields, polymers characterized by high xylene insolubility, a broad range of isotacticity and are further characterized by a good balance between hydrogen response and isotacticity.

Catalyst components for the stereospecific polymerization of olefins are widely known in the art. Basically two types of catalyst systems are used in the normal processes for the (co)polymerization of olefins. The first one, in its broadest definition, comprises TiCl_3 based catalysts components, obtained for example by reduction of TiCl_4 with Al-alkyls, used in combination with Al-compounds such as diethylaluminum chloride (DEAC). Despite the good properties of the polymers in terms of isotacticity said catalysts are characterized by a very low activity which causes the presence of large amounts of catalytic residues in the polymers. As a consequence, a further step of deashing is necessary to obtain a polymer having a content of catalytic residue that makes it acceptable for wide use. The second type of catalyst system comprises a solid catalyst component, constituted by a magnesium dihalide on which are supported a titanium compound and an internal electron donor compound, used in combination with an Al-alkyl compound. Conventionally however, when a higher crystallinity of the polymer is required, also an external donor (for example an alkoxysilane) is needed in order to obtain higher isotacticity. One of the

preferred classes of internal donors is constituted by the esters of phthalic acid, diisobutylphthalate being the most used. This catalyst system is capable to give very good performances in terms of activity, isotacticity and xylene insolubility provided that an external electron donor compound is used. In its absence, low yields, low xylene insolubility and poor isotacticity are obtained. On the other hand, when the external donor is used, high xylene insolubility is obtained only together with a high isotacticity. This is not desirable in certain applications, such as production of bi-oriented polypropylene films (BOPP), where polypropylenes are required to have a lower flexural modulus (obtainable by lowering crystallinity of the polymer) while at the same time retaining a high xylene insolubility. As a consequence, it would be desirable to have a catalyst component with still improved characteristics, particularly in terms of activity and isotacticity, as well a catalyst component capable to give polymers coupling high xylene insolubility with a slight lower crystallinity suitable for making the polymers usable in the BOPP sector.

Some improvements are obtained when, in the above mentioned catalyst system, the phthalates are substituted by the electron donor compounds disclosed for example in USP 4,971,937. In this case, the catalyst components obtained are capable to give better results when used in the absence of an external donor. In particular, the stereoregularity becomes acceptable, while however the xylene insolubility is still to be improved. Also in this case, when the catalyst component is used together with an external donor, high xylene insolubility is obtained only together with a high isotacticity.

It is therefore felt the need of a versatile catalyst component which, for high values of xylene insolubility, is capable to give polymers with a broader range of isotacticity.

Moreover, it would be also advantageous to have a catalyst component with still improved features in terms of activity and isotacticity.


It has now unexpectedly been found a catalyst component having the above advantages which comprises Mg, Ti, halogen and two electron donor compounds selected from specific classes.

It is therefore an object of the present invention a catalyst component for the polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising Mg, Ti, halogen and at least two electron donor compounds, said catalyst component being characterized by the fact that at least one of the electron donor compounds is selected from ethers containing two or more ether groups which are further characterized by the formation of complexes with anhydrous magnesium dichloride in an amount less than 60 mmols per 100 g of MgCl_2 and by the failure of entering into substitution reactions with TiCl_4 or by reacting in that way for less than 50% by moles, and at least another electron donor compound is selected from esters of mono or polycarboxylic acids.

The conditions under which, the reactivity toward titanium tetrachloride and the complexing activity of the di or polyethers are tested, are reported below.

Very surprisingly it has been found that the performances of the above-disclosed catalysts are not merely intermediate between those of the catalyst components containing the single donors. While we do not intend being bound to any theoretical interpretation, it can be said that a synergic interaction between the elements of the catalyst component, and maybe in particular between the above mentioned donors, is the basis for explaining the unexpected properties of the catalyst component of the invention.

Among the di or polyethers mentioned above, particularly preferred are the compounds belonging to the class of the 1,3-diethers. In particular, preferred 1,3-diethers are those of formula (I)




where R^{I} and R^{II} are the same or different and are hydrogen or linear or branched $\text{C}_1\text{-C}_{18}$ hydrocarbon groups which can also form one or more cyclic structures; R^{III} groups, equal or different from each other, are hydrogen or $\text{C}_1\text{-C}_{18}$ hydrocarbon groups; R^{IV} groups equal or different from each other, have the same meaning of R^{III} except that they cannot be hydrogen; each of R^{I} to R^{IV} groups can contain heteroatoms selected from halogens, N, O, S and Si.

Preferably, R^{IV} is a 1-6 carbon atom alkyl radical and more particularly a methyl while the R^{III} radicals are preferably hydrogen. Moreover, when R^{I} is methyl, ethyl, propyl, or isopropyl, R^{II} can be ethyl, propyl, isopropyl, butyl, isobutyl, tert-butyl, isopentyl, 2-ethylhexyl, cyclopentyl, cyclohexyl, methylcyclohexyl, phenyl or benzyl; when R^{I} is hydrogen, R^{II} can be ethyl, butyl, sec-butyl, tert-butyl, 2-ethylhexyl, cyclohexylethyl, diphenylmethyl, p-chlorophenyl, 1-naphthyl, 1-decahydronaphthyl; R^{I} and R^{II} can also be the same and can be ethyl, propyl, isopropyl, butyl, isobutyl, tert-butyl, neopentyl, phenyl, benzyl, cyclohexyl, cyclopentyl.

Specific examples of ethers that can be advantageously used include: 2-(2-ethylhexyl)-1,3-dimethoxypropane, 2-isopropyl-1,3-dimethoxypropane, 2-butyl-1,3-dimethoxypropane, 2-sec-butyl-1,3-dimethoxypropane, 2-cyclohexyl-1,3-dimethoxypropane, 2-phenyl-1,3-dimethoxypropane, 2-tert-butyl-1,3-dimethoxypropane, 2-cumyl-1,3-dimethoxypropane, 2-(2-phenylethyl)-1,3-dimethoxypropane, 2-(2-cyclohexylethyl)-1,3-dimethoxypropane, 2-(p-chlorophenyl)-1,3-dimethoxypropane, 2-(diphenylmethyl)-1,3-dimethoxypropane, 2(1-naphthyl)-1,3-dimethoxypropane, 2(p-fluorophenyl)-1,3-dimethoxypropane, 2(1-decahydronaphthyl)-1,3-dimethoxypropane, 2(p-tert-butylphenyl)-1,3-dimethoxypropane, 2,2-dicyclohexyl-1,3-dimethoxypropane, 2,2-diethyl-1,3-dimethoxypropane, 2,2-dipropyl-1,3-dimethoxypropane, 2,2-dibutyl-1,3-dimethoxypropane, 2,2-diethyl-1,3-diethoxypropane, 2,2-dicyclopentyl-1,3-dimethoxypropane, 2,2-dipropyl-1,3-diethoxypropane, 2,2-dibutyl-1,3-diethoxypropane, 2-methyl-2-ethyl-1,3-dimethoxypropane, 2-methyl-2-propyl-1,3-dimethoxypropane, 2-methyl-2-benzyl-1,3-dimethoxypropane, 2-methyl-2-phenyl-1,3-dimethoxypropane, 2-methyl-2-cyclohexyl-1,3-dimethoxypropane, 2-methyl-2-methylcyclohexyl-1,3-dimethoxypropane, 2,2-bis(p-chlorophenyl)-1,3-dimethoxypropane, 2,2-bis(2-phenylethyl)-1,3-dimethoxypropane, 2,2-bis(2-cyclohexylethyl)-1,3-dimethoxypropane, 2-methyl-2-isobutyl-1,3-dimethoxypropane, 2-methyl-2-(2-ethylhexyl)-1,3-dimethoxypropane, 2,2-bis(2-ethylhexyl)-1,3-dimethoxypropane, 2,2-bis(p-methylphenyl)-1,3-dimethoxypropane, 2-methyl-2-isopropyl-1,3-dimethoxypropane, 2,2-diisobutyl-1,3-dimethoxypropane, 2,2-diphenyl-1,3-dimethoxypropane, 2,2-dibenzyl-1,3-dimethoxypropane, 2-isopropyl-2-cyclopentyl-1,3-dimethoxypropane, 2,2-bis(cyclohexylmethyl)-1,3-dimethoxypropane, 2,2-diisobutyl-1,3-diethoxypropane, 2,2-diisobutyl-1,3-dibutoxypropane, 2-isobutyl-2-isopropyl-1,3-

dimethoxypropane, 2,2-di-sec-butyl-1,3-dimethoxypropane, 2,2-di-tert-butyl-1,3-dimethoxypropane, 2,2-dineopentyl-1,3-dimethoxypropane, 2-iso-propyl-2-isopentyl-1,3-dimethoxypropane, 2-phenyl-2-benzyl-1,3-dimethoxypropane, 2-cyclohexyl-2-cyclohexylmethyl-1,3-dimethoxypropane.


Furthermore, particularly preferred are the 1,3-diethers of formula (II)



(II)

where the radicals R^{IV} have the same meaning explained above and the radicals R^{III} and R^V radicals, equal or different to each other, are selected from the group consisting of hydrogen; halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkaryl and C_7 - C_{20} aralkyl radicals and two or more of the R^V radicals can be bonded to each other to form condensed cyclic structures, saturated or unsaturated, optionally substituted with R^VI radicals selected from the group consisting of halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkaryl and C_7 - C_{20} aralkyl radicals; said radicals R^V and R^VI optionally containing one or more heteroatoms as substitutes for carbon or hydrogen atoms, or both.

Preferably, in the 1,3-diethers of formulae (I) and (II) all the R^{III} radicals are hydrogen, and all the R^{IV} radicals are methyl. Moreover, are particularly preferred the 1,3-diethers of formula (II) in which two or more of the R^V radicals are bonded to each other to form one or more condensed cyclic structures, preferably benzenic, optionally substituted by R^{VI} radicals. Specially preferred are the compounds of formula (III):



(III)

where the R^{VI} radicals equal or different are hydrogen; halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkylaryl and C_7 - C_{20} aralkyl radicals, optionally containing one or more heteroatoms selected from the group consisting of N, O, S, P, Si and halogens, in particular Cl and F, as substitutes for carbon or hydrogen atoms, or both; the radicals R^{III} and R^{IV} are as defined above for formula (II).

Specific examples of compounds comprised in formulae (II) and (III) are:

1,1-bis(methoxymethyl)-cyclopentadiene;

1,1-bis(methoxymethyl)-2,3,4,5-tetramethylcyclopentadiene;


1,1-bis(methoxymethyl)-2,3,4,5-tetraphenylcyclopentadiene;

1,1-bis(methoxymethyl)-2,3,4,5-tetrafluorocyclopentadiene;
1,1-bis(methoxymethyl)-3,4-dicyclopentylcyclopentadiene;
1,1-bis(methoxymethyl)indene; 1,1-bis(methoxymethyl)-2,3-dimethylindene;
1,1-bis(methoxymethyl)-4,5,6,7-tetrahydroindene;
1,1-bis(methoxymethyl)-2,3,6,7-tetrafluoroindene;
1,1-bis(methoxymethyl)-4,7-dimethylindene;
1,1-bis(methoxymethyl)-3,6-dimethylindene;
1,1-bis(methoxymethyl)-4-phenylindene;
1,1-bis(methoxymethyl)-4-phenyl-2-methylindene;
1,1-bis(methoxymethyl)-4-cyclohexylindene;
1,1-bis(methoxymethyl)-7-(3,3,3-trifluoropropyl)indene;
1,1-bis(methoxymethyl)-7-trimethylsilylindene;
1,1-bis(methoxymethyl)-7-trifluoromethylindene;
1,1-bis(methoxymethyl)-4,7-dimethyl-4,5,6,7-tetrahydroindene;
1,1-bis(methoxymethyl)-7-methylindene;
1,1-bis(methoxymethyl)-7-cyclopentylindene;
1,1-bis(methoxymethyl)-7-isopropylindene;
1,1-bis(methoxymethyl)-7-cyclohexylindene;
1,1-bis(methoxymethyl)-7-tert-butylindene;
1,1-bis(methoxymethyl)-7-tert-butyl-2-methylindene;
1,1-bis(methoxymethyl)-7-phenylindene;
1,1-bis(methoxymethyl)-2-phenylindene;
1,1-bis(methoxymethyl)-1H-benz[e]indene;

1,1-bis(methoxymethyl)-1H-2-methylbenz[e]indene;
9,9-bis(methoxymethyl)fluorene;
9,9-bis(methoxymethyl)-2,3,6,7-tetramethylfluorene;
9,9-bis(methoxymethyl)-2,3,4,5,6,7-hexafluorofluorene;
9,9-bis(methoxymethyl)-2,3-benzofluorene;
9,9-bis(methoxymethyl)-2,3,6,7-dibenzofluorene;
9,9-bis(methoxymethyl)-2,7-diisopropylfluorene;
9,9-bis(methoxymethyl)-1,8-dichlorofluorene;
9,9-bis(methoxymethyl)-2,7-dicyclopentylfluorene;
9,9-bis(methoxymethyl)-1,8-difluorofluorene;
9,9-bis(methoxymethyl)-1,2,3,4-tetrahydrofluorene;
9,9-bis(methoxymethyl)-1,2,3,4,5,6,7,8-octahydrofluorene;
9,9-bis(methoxymethyl)-4-tert-butylfluorene.

As explained above, the other electron donor compound which must be present in the catalyst component of the invention has to be selected from the esters of mono or polycarboxylic acids. Said acids can be both aliphatic and aromatic acids.

Among esters of aliphatic acids, particularly preferred are the esters of bicarboxylic acids in particular esters of malonic acids. Particularly preferred are the esters of malonic acids of formula (IV):



where R_1 is H or a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_2 is a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_3 and R_4 , equal to, or different from, each other, are C_1 - C_{20} linear or branched alkyl groups or C_3 - C_{20} cycloalkyl groups.

Preferably, R_3 and R_4 are primary, linear or branched C_1 - C_{20} alkyl groups, more preferably they are primary branched C_4 - C_{20} alkyl groups such as isobutyl or neopentyl groups.

R_2 is preferably, in particular when R_1 is H, a linear or branched C_3 - C_{20} alkyl, cycloalkyl, or arylalkyl group; more preferably R_2 is a C_3 - C_{20} secondary alkyl, cycloalkyl, or arylalkyl group.

Specific examples of preferred monosubstituted malonate compounds are: dineopentyl 2-isopropylmalonate, diisobutyl 2-isopropylmalonate, di-n-butyl 2-isopropylmalonate, diethyl 2-dodecylmalonate, diethyl 2-t-butylmalonate, diethyl 2-(2-pentyl)malonate, diethyl 2-cyclohexylmalonate, dineopentyl 2-t-butylmalonate, dineopentyl 2-isobutylmalonate, diethyl 2-cyclohexylmethylmalonate, dimethyl 2-cyclohexylmethylmalonate.

Specific examples of preferred disubstituted malonates compounds are: diethyl 2,2-dibenzylmalonate, diethyl 2-isobutyl-2-cyclohexylmalonate, dimethyl 2-n-butyl-2-isobutylmalonate, diethyl 2-n-butyl-2-isobutylmalonate, diethyl 2-isopropyl-2-n-butylmalonate, diethyl 2-methyl-2-isopropylmalonate, diethyl 2-isopropyl-2-isobutylmalonate, diethyl 2-methyl-2-isobutylmalonate, diethyl 2-isobutyl-2-benzylmalonate.

Preferred esters of aromatic carboxylic acids are selected from C_1 - C_{20} alkyl or aryl esters of benzoic and phthalic acids, possibly substituted. The alkyl esters of the said acids being preferred. Particularly preferred are the C_1 - C_6 linear or branched alkyl esters. Specific examples are ethylbenzoate, n-butylbenzoate, p-methoxy ethylbenzoate, p-ethoxy ethylbenzoate, isobutylbenzoate, ethyl p-toluate, diethyl phthalate, di-n-propyl phthalate, di-n-butyl phthalate, di-n-pentyl phthalate, di-i-pentyl phthalate, bis(2-ethylhexyl) phthalate, ethyl-isobutyl phthalate, ethyl-n-butyl phthalate, di-n-hexyl phthalate, di-isobutylphthalate.

As explained above, the catalyst components of the invention comprise, in addition to the above electron donors, Ti, Mg and halogen. In particular, the catalyst components comprise a titanium compound, having at least a Ti-halogen bond and the above mentioned electron donor compounds supported on a Mg halide. The magnesium halide is preferably $MgCl_2$ in active form which is widely known from the patent literature as a support for Ziegler-Natta catalysts. Patents USP 4,298,718 and USP 4,495,338 were the first to describe the use of these compounds in Ziegler-Natta catalysis.. It is known from these patents that the magnesium dihalides in active form used as support or co-support in components of catalysts for the polymerization of olefins are characterized by X-ray spectra in which the most intense diffraction line that appears in the spectrum of the non-active halide is diminished in intensity and is replaced by a halo whose maximum intensity is displaced towards lower angles relative to that of the more intense line.

The preferred titanium compounds used in the catalyst component of the present invention are $TiCl_4$ and $TiCl_3$; furthermore, also Ti-haloalcoholates of formula $Ti(OR)_{n-y}X_y$ can be

used, where n is the valence of titanium, y is a number between 1 and $n-1$ X is halogen and R is a hydrocarbon radical having from 1 to 10 carbon atoms.

The preparation of the solid catalyst component can be carried out according to several methods. According to one of these methods, the magnesium dichloride in an anhydrous state, the titanium compound and the electron donor compounds are milled together under conditions in which activation of the magnesium dichloride occurs. The so obtained product can be treated one or more times with an excess of $TiCl_4$ at a temperature between 80 and 135°C. This treatment is followed by washings with hydrocarbon solvents until chloride ions disappeared. According to a further method, the product obtained by co-milling the magnesium chloride in an anhydrous state, the titanium compound and the electron donor compounds are treated with halogenated hydrocarbons such as 1,2-dichloroethane, chlorobenzene, dichloromethane etc. The treatment is carried out for a time between 1 and 4 hours and at temperature of from 40°C to the boiling point of the halogenated hydrocarbon. The product obtained is then generally washed with inert hydrocarbon solvents such as hexane.

According to another method, magnesium dichloride is preactivated according to well known methods and then treated with an excess of $TiCl_4$ at a temperature of about 80 to 135°C in the presence of the electron donor compounds. The treatment with $TiCl_4$ is repeated and the solid is washed with hexane in order to eliminate any non-reacted $TiCl_4$.

A further method comprises the reaction between magnesium alcoholates or chloroalcoholates (in particular chloroalcoholates prepared according to USP 4,220,554) and an excess of $TiCl_4$ in the presence of the electron donor compounds at a temperature of about 80 to 120°C.

According to a preferred method, the solid catalyst component can be prepared by reacting a titanium compound of formula $\text{Ti}(\text{OR})_n\text{X}_y$, where n is the valence of titanium and y is a number between 1 and n , preferably TiCl_4 , with a magnesium chloride deriving from an adduct of formula MgCl_2pROH , where p is a number between 0.1 and 6, preferably from 2 to 3.5, and R is a hydrocarbon radical having 1-18 carbon atoms. The adduct can be suitably prepared in spherical form by mixing alcohol and magnesium chloride in the presence of an inert hydrocarbon immiscible with the adduct, operating under stirring conditions at the melting temperature of the adduct (100-130°C). Then, the emulsion is quickly quenched, thereby causing the solidification of the adduct in form of spherical particles. Examples of spherical adducts prepared according to this procedure are described in USP 4,399,054 and USP 4,469,648. The so obtained adduct can be directly reacted with Ti compound or it can be previously subjected to thermal controlled dealcoholation (80-130°C) so as to obtain an adduct in which the number of moles of alcohol is generally lower than 3 preferably between 0.1 and 2.5. The reaction with the Ti compound can be carried out by suspending the adduct (dealcoholated or as such) in cold TiCl_4 (generally 0°C); the mixture is heated up to 80-130°C and kept at this temperature for 0.5-2 hours. The treatment with TiCl_4 can be carried out one or more times. The electron donor compounds can be added during the treatment with TiCl_4 . They can be added together in the same treatment with TiCl_4 or separately in two or more treatments.

The preparation of catalyst components in spherical form are described for example in European Patent Applications EP-A-395083, EP-A-553805, EP-A-553806, EPA601525 and WO98/44001.

The solid catalyst components obtained according to the above method show a surface area (by B.E.T. method) generally between 20 and 500 m²/g and preferably between 50 and 400 m²/g, and a total porosity (by B.E.T. method) higher than 0.2 cm³/g preferably between 0.2 and 0.6 cm³/g. The porosity (Hg method) due to pores with radius up to 10.000Å generally ranges from 0.3 to 1.5 cm³/g, preferably from 0.45 to 1 cm³/g.

A further method to prepare the solid catalyst component of the invention comprises halogenating magnesium dihydrocarbyloxy compounds, such as magnesium dialkoxide or diaryloxy, with solution of TiCl₄ in aromatic hydrocarbon (such as toluene, xylene etc.) at temperatures between 80 and 130°C. The treatment with TiCl₄ in aromatic hydrocarbon solution can be repeated one or more times, and the electron donor compounds are added during one or more of these treatments.

In any of these preparation methods the desired electron donor compounds and in particular those selected from esters of carboxylic acids, can be added as such or, in an alternative way, it can be obtained *in situ* by using an appropriate precursor capable to be transformed in the desired electron donor compound by means, for example, of known chemical reactions such as esterification, transesterification, etc.

Regardless to the preparation method used, the final amount of the two or more electron donor compounds is such that the molar ratio with respect to the MgCl₂ is from 0.01 to 1, preferably from 0.05 to 0.5, while the molar ratio between the di or polyether donor and the ester donor is comprised in the range of from 50 to 0.02 preferably from 30 to 0.1 and more preferably from 20 to 0.2.

The solid catalyst components according to the present invention are converted into catalysts for the polymerization of olefins by reacting them with organoaluminum compounds according to known methods.

In particular, it is an object of the present invention a catalyst for the polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction between:


- (i) the solid catalyst component as disclosed above and
- (ii) an alkylaluminum compound.

The alkyl-Al compound (ii) is preferably chosen among the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. It is also possible to use alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides, such as AlEt_2Cl and $\text{Al}_2\text{Et}_3\text{Cl}_3$, possibly in mixture with the above cited trialkylaluminums.

As explained above, the catalyst component of the invention when used in the polymerization of propylene in the absence of external donors are able to give polymers with a controlled wide range of isotacticity (expressed in term of percentage of mmmm pentads) while maintaining high xylene insolubility levels.

Furthermore, the catalyst components of the invention can also be used in combination with an external donor (iii) thereby obtaining very high values of both xylene insolubility and isotacticity. In particular, said values, individually or as a balance, are higher than the values obtainable with the catalyst containing the single donors.

Suitable external electron-donor compounds include silicon compounds, ethers, esters, amines, heterocyclic compounds and particularly 2,2,6,6-tetramethyl piperidine, ketones and the 1,3-diethers of the general formula (V):



wherein R^{I} , R^{II} , R^{III} , R^{IV} , R^{V} and R^{VI} equal or different to each other, are hydrogen or hydrocarbon radicals having from 1 to 18 carbon atoms, and R^{VII} and R^{VIII} , equal or different from each other, have the same meaning of $\text{R}^{\text{I}}-\text{R}^{\text{VI}}$ except that they cannot be hydrogen; one or more of the $\text{R}^{\text{I}}-\text{R}^{\text{VIII}}$ groups can be linked to form a cycle. Particularly preferred are the 1,3-diethers in which R^{VII} and R^{VIII} are selected from C_1-C_4 alkyl radicals.

Another class of preferred external donor compounds is that of silicon compounds of formula $\text{R}_a^5\text{R}_b^6\text{Si}(\text{OR}^7)_c$, where a and b are integers from 0 to 2, c is an integer from 1 to 3 and the sum (a+b+c) is 4; R^5 , R^6 , and R^7 , are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms. Particularly preferred are the silicon compounds in which a is 1, b is 1, c is 2, at least one of R^5 and R^6 is selected from branched alkyl, cycloalkyl or aryl groups with 3-10 carbon atoms optionally containing heteroatoms and R^7 is a C_1-C_{10} alkyl group, in particular methyl. Examples of such preferred silicon compounds are methylcyclohexyldimethoxysilane, diphenyldimethoxysilane, methyl-t-butyldimethoxysilane, dicyclopentyldimethoxysilane, (2-ethylpiperidiny)l-t-butyldimethoxysilane, (2-ethylpiperidiny)l-thexyldimethoxysilane, (3,3,3-trifluoro-n-propyl)(2-ethylpiperidiny)ldimethoxysilane, methyl(3,3,3-trifluoro-n-propyl)dimethoxysilane.

Moreover, are also preferred the silicon compounds in which a is 0, c is 3, R⁶ is a branched alkyl or cycloalkyl group, optionally containing heteroatoms, and R⁷ is methyl. Examples of such preferred silicon compounds are cyclohexyltrimethoxysilane, t-butyltrimethoxysilane and hexyltrimethoxysilane.

The electron donor compound (iii) is used in such an amount to give a molar ratio between the organoaluminum compound and said electron donor compound (iii) of from 0.1 to 500, preferably from 1 to 300 and more preferably from 3 to 100.

Therefore, it constitutes a further object of the present invention a process for the (co)polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, carried out in the presence of a catalyst comprising the product of the reaction between:

- (i) a solid catalyst component comprising a titanium compound, having at least a Ti-halogen bond, and at least two electron donor compounds supported on a Mg halide said catalyst being characterized by the fact that at least one of the electron donors compounds is selected from ethers containing two or more ether groups which are further characterized by the formation of complexes with anhydrous magnesium dichloride in an amount less than 60 mmols per 100 g of MgCl₂ and by the failure of entering into substitution reactions with TiCl₄ or by reacting in that way for less than 50% by moles, and at least another electron donor compound is selected from esters of mono or polycarboxylic acids;
- (ii) an alkylaluminum compound and,
- (iii) optionally an electron-donor compound (external donor).

The polymerization process can be carried out according to known techniques for example slurry polymerization using as diluent an inert hydrocarbon solvent, or bulk polymerization using the liquid monomer (for example propylene) as a reaction medium. Moreover, it is possible to carry out the polymerization process in gas-phase operating in one or more fluidized or mechanically agitated bed reactors.

The polymerization is generally carried out at temperature of from 20 to 120°C, preferably of from 40 to 80°C. When the polymerization is carried out in gas-phase the operating pressure is generally between 0.5 and 5 MPa, preferably between 1 and 4 MPa. In the bulk polymerization the operating pressure is generally between 1 and 8 MPa preferably between 1.5 and 5 MPa.

The following examples are given in order to better illustrate the invention without limiting it.

CHARACTERIZATIONS

Complexing test of the ethers with MgCl₂

In a 100 ml glass flask with fixed blades mechanical stirrer are introduced under nitrogen atmosphere in order:

- 70 ml of anhydrous n-heptane
- 12 mmoles of anhydrous MgCl₂ activated as described below
- 2 mmoles of ether.

The content is allowed to react at 60°C for 4 hours (stirring speed at 400 rpm). It is then filtered and washed at ambient temperature with 100 ml of n-heptane after which it is dried with a mechanical pump.

The solid is characterized, after having been treated with 100 ml of ethanol, by way of a

gaschromatographic quantitative analysis for the analysis of the quantity of ether fixed.

The magnesium chloride used in the complexing test with the ethers is prepared as follows.

In a 1 liter vibrating mill jar (Vibratom from Siebtechnik) containing 1.8 Kg of steel spheres 16 mm in diameter, are introduced under nitrogen atmosphere, 50 g of anhydrous MgCl_2 and 6.8 ml of 1,2-dichloroethane (DCE).

The content is milled at room temperature for 96 hours, after which the solid recovered is kept under vacuum in the mechanical pump for 16 hours at 50°C.

Characterization of the solid:

Presence of a halo with maximum intensity at $2\theta = 32.1^\circ$.

Surface area (B.E.T) = 125 m^2/g

residual DCE = 2.5% by weight.

Test of the reaction with TiCl_4

In a 25 ml test-tube with a magnetic stirrer and under nitrogen atmosphere are introduced: 10 ml of anhydrous n-heptane, 5 mmoles of TiCl_4 and 1 mmole of donor. The content is allowed to react at 70°C for 30 minutes, after which it is cooled to 25°C and decomposed with 90 ml of ethanol.

The solutions obtained are analyzed by gaschromatography.

Polymer microstructure analysis

50 mg of each xylene insoluble fraction were dissolved in 0.5 ml of $\text{C}_2\text{D}_2\text{Cl}_4$.

The ^{13}C NMR spectra were acquired on a Bruker DPX-400 (100.61 Mhz, 90° pulse, 12s delay between pulses). About 3000 transients were stored for each spectrum; mmmm pentad peak (21.8 ppm) was used as reference.

The microstructure analysis was carried out as described in literature (*Polymer*, 1984, 25,

1640, by Inoue Y. et Al. and Polymer, 1994, 35, 339, by Chujo R. et Al.).

Determination of X.I.

2.5 g of polymer were dissolved in 250 ml of o-xylene under stirring at 135°C for 30 minutes, then the solution was cooled to 25°C and after 30 minutes the insoluble polymer was filtered. The resulting solution was evaporated in nitrogen flow and the residue was dried and weighed to determine the percentage of soluble polymer and then, by difference, the X.I. %.

Examples

Examples 1-7 and comparative examples C1-C4

Preparation of Solid Catalyst Components

Into a 1000 ml five-necked flask, purged with nitrogen, 800 ml of TiCl_4 were introduced at 0°C. While stirring, 40.0g of microspheroidal $\text{MgCl}_2 \cdot 2.1\text{C}_2\text{H}_5\text{OH}$ (obtained by partial Thermal dealcoholation of an adduct prepared as described in ex. 2 of USP 4,399,054 but operating at 3,000 rpm instead of 10,000) were introduced. As internal donor(s), a mixture of diether + ester or a diether or an ester were also added. Type(s) of internal donor(s) and amount(s) are reported in Table 1.

The temperature was raised to 110°C and kept for 60 min. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off.

800 ml of fresh TiCl_4 and a mixture of diether + ester or a diether or an ester, type(s) and amount(s) are reported in Table 1, were added and reacted under stirring at 110°C for 30 min; then, the supernatant liquid was siphoned off.

800 ml of fresh TiCl_4 were added, the mixture was maintained under agitation at 110°C for

30 min. and then the supernatant liquid was siphoned off. The solid was washed five times (5 x 300 ml) at 60°C and three times (3 x 300 ml) at room temperature with anhydrous hexane. The solid was finally dried under vacuum and analyzed. The amount of Ti, internal donors and Diether/Ester molar ratio in the solid catalyst component are reported in Table 1.

Polymerization Examples 8-12 and comparative examples C5-C6

Polymerization of propylene by using solid catalyst components of examples 1-4, 7 and C1-C2.

In a 4 liter autoclave, purged with nitrogen flow at 70°C for one hour, 75 ml of anhydrous hexane containing 600 mg of AlEt₃ and 6 mg of solid catalyst component were introduced in propylene flow at 30°C. The autoclave was closed, 1.0 Nl of hydrogen was added and then, under stirring, 1,2 Kg of liquid propylene were fed. The temperature was raised to 70°C in five minutes and the polymerization was carried out at this temperature for two hours. The nonreacted propylene was removed, the polymer was recovered and dried at 70°C under vacuum for three hours, and then weighed and fractionated with o-xylene to determine the amount of the xylene insoluble (X.I.) fraction. The xylene insoluble fraction was further characterized with ¹³C-NMR to determine the value of mmmm%. The results are reported in Table 2.

Comparative example C7

By using the solid catalyst component of the comparative example C2, propylene was polymerized using the procedure described in examples 8-12 and C5-C6, but, in this case, as external donor 0.0026 mmoles of 9,9-bis(methoxymethyl)fluorene were added. The results are reported in Table 2

Polymerization Examples 13-19 and comparative examples C8-C11

By using the solid catalyst components of examples 1-7 and C1-C4, propylene was polymerized using the procedure described in the examples 8-12 and C5-C6, but, in this case as external donor 0.27 mmoles of Dicyclopentyldimethoxysilane were added and 1.5 NI of hydrogen were used. The results are reported in Table 2

Examples 20-21 and comparative examples C12-C13**Preparation of Solid Catalyst Components**

Into a 1000 ml five-necked flask, purged with nitrogen, 800 ml of TiCl_4 were introduced at 0°C . While stirring, 32.0g of microspheroidal $\text{MgCl}_2 \cdot 2.8\text{C}_2\text{H}_5\text{OH}$ (prepared according the method described in as described. ex. 2 of USP 4,399,054 but operating at 3,000 rpm instead of 10,000) were introduced. As internal donor(s), a mixture of diether + ester or a diether or an ester were also added. Type(s) of internal donor(s) and amount(s) are reported in Table 3

The temperature was raised to 110°C and maintained for 60 min. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off.

800 ml of fresh TiCl_4 and a mixture of diether + ester or a diether or an ester, type(s) and amount(s) are reported in Table 1, were added and reacted under stirring at 110°C for 30 min; then, the supernatant liquid was siphoned off.

800 ml of fresh TiCl_4 were added, the mixture was maintained under agitation at 110°C for 30 min. and then the supernatant liquid was siphoned off. The solid was washed five times (5 x 300 ml) at 60°C and three times (3 x 300 ml) at room temperature with anhydrous hexane. The solid was finally dried under vacuum and analyzed. The amount of Ti, I.D.'s

and Diether /Ester molar ratio in the solid catalyst component are reported in Table 3.

Examples 22-23 and comparative examples C14-C15

By using the solid catalyst components of examples 20-21 and C12-C13, polymerizations were carried out with the same procedure described in the examples 8-12 and C5-C6. The result are reported in Table 4

Examples 24-25 and comparative examples C16-C17

By using the solid catalyst components of examples 20-21 and C12-C13, propylene was polymerized with the same procedure described in the examples 13-19 and C8-C11. The results are reported in Table 4

Examples 26-27 and comparative examples C18-C19

Polymerizations were conducted by using the solid catalyst components of examples 20-21 and C12-C13.

In a 4 liter autoclave, purged with nitrogen flow at 70°C for one our, 75 ml of anhydrous hexane containing 830 mg of AlEt₃, 330 mg of AlEt₂Cl, 560 mg of ethyl-p-ethoxybenzoate and 6 mg of solid catalyst component were introduced in propylene flow at 30°C. The autoclave was closed, 1.5 Nl of hydrogen were added and then, under stirring, 1,2 Kg of liquid propylene were fed. The temperature was raised to 70°C in five minutes and the polymerization was carried out at this temperature for two hours. The nonreacted propylene was removed, the polymer was recovered and dried at 70°C under vacuum for three hours, and then weighed and fractionated with o-xylene to determine the amount of the xylene insoluble fraction (X.I.). The xylene insoluble fraction was further characterized with ¹³C-NMR to determine the value of mmmm%. The results are reported in Table 4.

TABLE I

PREPARATION CONDITIONS										COMPOSITION			
Example	I st Titration			II nd Titration			Ti	Diether	Ester	Diether/Ester			
N°	Diether type	mmols	Ester type	mmols	Diether type	mmols	Ester type	mmols	wt%	wt%	m.r.		
1	A	26.1	DIBP	2.1	A	26.1	DIBP	2.1	4.2	13.7	1.1	13.6	
2	""	23.2	""	8.7	""	11.6	""	4.4	3.7	15.3	5.3	3,2	
3	""	23.2	""	17.4	""	11.6	""	8.7	3.7	7.6	7.6	1.1	
4	""	17.4	""	26.1	""	8.7	""	13.1	4.6	9.3	13.7	0.7	
5	""	2.6	""	17.4	""	2.6	""	8.7	3.1	2.6	10.7	0.3	
6	B	23.2	DIBP	17.4	B	11.6	DIBP	8.7	4.5	7.6	7.2	1.5	
7	A	23.2	DTBM	17.4	A	11.6	DTBM	8.7	3.9	12.0	10.4	1.0	
C1	A	23.2	-----	---	A	11.6	--	---	5.5	13.9	---	---	
C2	-----	---	DIBP	17.4	--	---	DIBP	8.7	2.8	---	8.8	---	
C3	B	23.2	-----	---	B	11.6	--	---	3.8	11.8	---	---	
C4	-----	---	DTBM	23.2	--	---	DTBM	11.6	3.3	---	12.1	---	

A= 9,9-bis(methoxymethyl)fluorene

B= 2-isobutyl-2-isopropyl-1,3-dimethoxypropane

DIBP= diisobutylphthalate

DTBM= Diethyl-2-tertbutylmalonate

TABLE 2

Polymerization Example.	Catalyst Ex.	Yield	X.I.	mmmm
n.	n.	Kg/g	%	%
8	1	118	97.2	97.6
9	2	96	96.6	96.6
10	3	54	97.0	96.4
11	4	57	95.6	96.1
12	7	60	97.2	97,1
C.5	C. 1	90	95.3	96.1
C.6	C. 2	24	63.0	82.9
C.7	C. 2	38	82.6	92.5
13	1	86	98.8	98.4
14	2	70	98.8	98.1
15	3	52	98.6	98.7
16	4	57	98.2	98.3
17	5	52	98.8	97.8
18	6	38	98.8	97.7
19	7	51	99.0	98.3
C.8	C.1	70	98.4	97.7
C.9	C.2	50	98.0	98.9
C.10	C.3	40	98.5	n.d.
C.11	C.4	27	97,0	97.3

TABLE 3

PREPARATION CONDITIONS										COMPOSITION			
Example	I st Titination				II nd Titination				Ti				
N°	Diether type	mmols	Ester type	mmols	Diether type	mmols	Ester type	mmols	wt%	Diether wt%	Ester wt%	Diether/Ester	m.r.
20	A	15.9	EB	35.8	A	7.9	EB	15.9	3	22.4	4.0	3.3	
21	"	15.9	"	95.3	"	7.9	--	--	3.7	10.7	7.0	0.9	
C12	"	15.9	--	--	"	7.9	--	--	5.2	17.7	---	---	
C13	---	--	EB	95.3	--	--	--	--	3.9	--	15.7	---	


EB= ethylbenzoate

TABLE 4

Polymerization Example.	Catalyst Ex.	Yield	X.I.	mmmm
n.	n.	Kg/g	%	%
22	20	130	97.1	96.5
23	21	121	96.5	95.9
C14	C12	130	95.1	96.2
C15	C13	58	41.5	80.3
24	20	95	99	98.3
25	21	94	98.8	97.9
C16	C12	100	98.2	97.7
C17	C13	51	91.2	n.d.
26	20	41	99.3	98.2
27	21	64	98.8	98.1
C18	C12	39	98.5	n.d.
C19	C13	25	95.5	95.5

CLAIMS


1. Catalyst component for the polymerization of olefins $\text{CH}_2=\text{CHR}$ in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising Mg, Ti, halogen and at least two electron donor compounds, said catalyst being characterized by the fact that at least one of the electron donor compounds is selected from ethers containing two or more ether groups which are further characterized by the formation of complexes with anhydrous magnesium dichloride in an amount less than 60 mmoles per 100 g of MgCl_2 and by the failure of entering into substitution reactions with TiCl_4 or by reacting in that way for less than 50% by moles, and at least another electron donor compound is selected from esters of mono or polycarboxylic acids.
2. Catalyst component according to claim 1 in which the ethers are selected from 1,3-diethers.
3. Catalyst components according to claim 2 in which the 1,3-diethers are selected from those of formula (I)



where R^{I} and R^{II} are the same or different and are hydrogen or linear or branched C_1 - C_{18} hydrocarbon groups which can also form one or more cyclic structures; R^{III} groups, equal or different from each other, are hydrogen or C_1 - C_{18} hydrocarbon groups; R^{IV} groups equal or different from each other, have the same meaning of R^{III} except that

they cannot be hydrogen; each of R^I to R^{IV} groups can contain heteroatoms selected from halogens, N, O, S and Si.


4. Catalyst component according to claim 3 in which the 1,3-diethers are selected from those of formula (II)



(II)

where the radicals R^{IV} have the same meaning explained above and the radicals R^{III} and R^V radicals, equal or different are selected from the group consisting of hydrogen; halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkaryl and C_7 - C_{20} aralkyl radicals and two or more of the R^V radicals can be bonded to each other to form condensed cyclic structures, saturated or unsaturated, optionally substituted with R^{VI} , radicals selected from the group consisting of halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkaryl and C_7 - C_{20} aralkyl radicals; said radicals R^V and R^{VI} optionally containing one or more heteroatoms as substitutes for carbon or hydrogen atoms, or both.


5. Catalyst components according to the claims 3-4 in which the R^{III} radicals are hydrogen, and all the R^{IV} radicals are methyl.
6. Catalyst according to claim 4 in which two or more of the R^V radicals can be bonded to each other to form one or more condensed cyclic structures.
7. Catalyst components according to claim 6 in which the 1,3-diethers are selected from the compounds of formula (III):



(III)

where the R^{VI} radicals equal or different are hydrogen; halogens, preferably Cl and F; C_1 - C_{20} alkyl radicals, linear or branched; C_3 - C_{20} cycloalkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkylaryl and C_7 - C_{20} aralkyl radicals, optionally containing one or more heteroatoms selected from the group consisting of N, O, S, P, Si and halogens, in particular Cl and F, as substitutes for carbon or hydrogen atoms, or both; the radicals R^{III} and R^{IV} are as defined above for formula (II).

8. Catalyst according to claim 1 in which the ester electron donor compound is selected from esters of aliphatic dicarboxylic acids.
9. Catalyst according to claim 8 in which said esters are esters of malonic acids of formula (IV):




where R_1 is H or a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_2 is a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_3 and R_4 , equal to, or different from, each other, are C_1 - C_{20} linear or branched alkyl groups or C_3 - C_{20} cycloalkyl groups.

10. Catalyst components according to claim 1 in which the ester electron donor compound is selected from esters of aromatic carboxylic acids.
11. Catalyst according to claim 10 in which the esters of aromatic carboxylic acids are selected from C_1 - C_{20} alkyl or aryl esters of benzoic and phthalic acids, possibly substituted.
12. Catalyst components according to claim 11 in which said esters are C_1 - C_6 linear or branched alkyl esters.
13. Catalyst components according to any of the preceding claims in which the molar ratio between the di or polyether donor and the ester donor is comprised in the range of from 0.02 to 50.

14. Catalyst components according to claim 13 in which the molar ratio between the di or polyether donor and the ester donor is from 0.1 to 30.
15. Catalyst components according to any of the preceding claims comprising a titanium compound having at least a Ti-halogen bond and the at least two different electron donor compounds supported on a Mg halide in active form.
16. Catalyst components according to claim 15 in which the titanium compound is selected from TiCl_4 and TiCl_3 .
17. A solid catalyst component according to claim 1 having a spherical form, a surface area (by B.E.T. method) between 20 and 500 m^2/g , and a total porosity (by B.E.T. method) higher than 0.2 cm^3/g .
18. Catalyst for the polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction between:
 - (i) the solid catalyst component according to any of the preceding claims and
 - (ii) an alkylaluminum compound.
19. Catalyst according to claim 18 further comprising an external electron donor compound.

Catalyst according to claim 19 in which the external electron donor compound is selected from ethers, esters, amines, heterocyclic compounds and particularly 2,2,6,6-tetramethyl piperidine, ketones and the 1,3-diethers of the general formula (V):



wherein R^{I} , R^{II} , R^{III} , R^{IV} , R^{V} and R^{VI} equal or different to each other, are hydrogen or hydrocarbon radicals having from 1 to 18 carbon atoms, and R^{VII} and R^{VIII} , equal or different from each other, have the same meaning of $\text{R}^{\text{I}}\text{-R}^{\text{VI}}$ except that they cannot be hydrogen; one or more of the $\text{R}^{\text{I}}\text{-R}^{\text{VIII}}$ groups can be linked to form a cycle. Particularly preferred are the 1,3-diethers in which R^{VII} and R^{VIII} are selected from $\text{C}_1\text{-C}_4$ alkyl radicals.

20. Catalyst according to claim 19 in which the electron donor compound is selected from silicon compounds of formula $\text{R}_a^5\text{R}_b^6\text{Si}(\text{OR}^7)_c$, where a and b are integer from 0 to 2, c is an integer from 1 to 4 and the sum (a+b+c) is 4; R^5 , R^6 and R^7 are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms..
21. Catalyst according to claim 21 in which a is 1, b is 1 and c is 2.
22. Catalyst according to claim 22 in which R^5 and/or R^6 are branched alkyl, cycloalkyl or aryl groups with 3-10 carbon atoms optionally containing heteroatoms and R^7 is a $\text{C}_1\text{-C}_{10}$ alkyl group, in particular methyl.
23. Catalyst according to claim 21 in which a is 0, c is 3 and R^6 is a branched alkyl or cycloalkyl group and R^7 is methyl.

24. Catalyst according to claim 22 in which the silicon compound is selected from the group consisting of methylcyclohexyldimethoxysilane, diphenyldimethoxysilane, methyl-t-butyl dimethoxysilane, dicyclopentyldimethoxysilane, (2-ethylpiperidiny)l-t-butyl dimethoxysilane, (2-ethylpiperidiny)lthexyldimethoxysilane, (3,3,3-trifluoro-n-propyl)(2-ethylpiperidiny)ldimethoxysilane, methyl(3,3,3-trifluoro-n-propyl)dimethoxysilane
25. Process for the (co)polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, carried out in the presence of a catalyst comprising the product of the reaction between:
- (i) the solid catalyst component according to any of the proceeding claims;
 - (ii) an alkylaluminum compound and,
 - (iii) optionally an external donor compound.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/02914

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F4/651 C08F4/654 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 452 156 A (MITSUI PETROCHEMICAL IND) 16 October 1991 (1991-10-16)	1-3, 10-12, 15,16, 18,25
Y	claims 1,4 examples 7,8	4-7
X	page 7, line 22 - line 50 page 8, line 2 - line 3	8,9
X	examples 9,11	19
X	page 16, line 44 - line 49	20
X	page 9, line 26 - line 55	20-24
Y	EP 0 728 770 A (MONTELL NORTH AMERICA INC) 28 August 1996 (1996-08-28) example 1 comparative example 7	4-7

-/-

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

1 September 1999

Date of mailing of the international search report

13/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fischer, B

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/EP 99/02914

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 585 869 A (MITSUI PETROCHEMICAL IND) 9 March 1994 (1994-03-09)	1-3,5, 10-12, 15,16, 18-25
A	claims 1,9 page 8, line 48 - page 9, line 2 page 12, line 36 - page 14, line 53 example 1	1
P,X	EP 0 896 969 A (MITSUI CHEMICALS INC) 17 February 1999 (1999-02-17)	1-3,5, 10-16, 18-25
P,X	example 10 page 6, line 26 - line 51	9,10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02914

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0452156 A	16-10-1991	JP 3294304 A	25-12-1991
		AT 156843 T	15-08-1997
		CA 2040336 A,C	14-10-1991
		CN 1057656 A,B	08-01-1992
		DE 69127220 D	18-09-1997
		DE 69127220 T	02-01-1998
		GR 3024753 T	31-12-1997
		JP 4218508 A	10-08-1992
		KR 9406215 B	13-07-1994
		US 5726262 A	10-03-1998
		JP 4218509 A	10-08-1992
		JP 4218510 A	10-08-1992
EP 0728770 A	28-08-1996	IT MI950319 A	21-08-1996
		CN 1141303 A	29-01-1997
		DE 69603211 D	19-08-1999
		JP 9020804 A	21-01-1997
		US 5723400 A	03-03-1998
EP 0585869 A	09-03-1994	JP 6336503 A	06-12-1994
		CA 2105119 A,C	01-03-1994
		CN 1087094 A,B	25-05-1994
		CZ 9301790 A	16-03-1994
		DE 69311033 D	03-07-1997
		DE 69311033 T	16-10-1997
		HU 68333 A	28-06-1994
		KR 142072 B	01-07-1998
		US 5780378 A	14-07-1998
		US 5877265 A	02-03-1999
		CZ 9503308 A	11-09-1996
EP 0896969 A	17-02-1999	CN 1208045 A	17-02-1999